

## **OmegaAntiRust (series 80)**

*High quality solvent base red oxide metal primer  
For exterior & interior use*

<b>CHARACTERISTICS</b>	OmegaAntiRust Red Oxide Anti-Corrosion Metal Primer is a solvent-based sealer, anti-corrosive protective primer for interior and exterior ferrous and non-ferrous metal work including steelwork, new weathered and pre-tested zinc and galvanized iron. It may also be applied over pre-treated aluminium.									
<b>SURFACE PREPARATION</b>	Surface generally must be clean, dry, free from all defective or poorly adhering material, dirt, and grease, wax etc. previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dusted off. For optimum performance new galvanized surfaces should be cleaned and degreased, then pre-treated with an appropriate pre-treatment primer to ensure good adhesion.									
<b>APPLICATION</b>	Can be done by brush, roller or airless spray.									
<b>THINNING</b>	Use mineral spirit up to 20 % for brush or roller application and up to 30 % for airless spray application.									
<b>COVERAGE</b>	In normal application 40 – 50 meter square per U.S. Gallon for one coat, it may reach up to 60 meter square depending on surface absorption.									
<b>DRYING TIME</b>	<table><tr><td>Dry to touch (Dust Free)</td><td>1 – 2</td><td>Hours.</td></tr><tr><td>Dry to re-coat</td><td>4 – 6</td><td>Hours.</td></tr><tr><td>Dry to handle</td><td>12 - 24</td><td>Hours.</td></tr></table>	Dry to touch (Dust Free)	1 – 2	Hours.	Dry to re-coat	4 – 6	Hours.	Dry to handle	12 - 24	Hours.
Dry to touch (Dust Free)	1 – 2	Hours.								
Dry to re-coat	4 – 6	Hours.								
Dry to handle	12 - 24	Hours.								