

OmegaTan (series 800) *Acrylic Emulsion Paint, Humidity Killer*

CHARACTERISTICS: An emulsion paints which would be used on concrete walls, ceiling and putty filler with outstanding durability in various weathering conditions. This remarkable new flat paint is recommended for all areas where a true flat finish is desired, it repels airborne dust dirt which will collect on all wall surfaces. Resistance to humidity and alkalinity of concrete, perfect adhesion and inter-coat adhesion ease of application, non-toxicity, scrub-able with salt and water and is free from disagreeable odor. It qualifies for safety painting slightly damp or permeable surface because it allows the humidity to pass through.

SURFACE PREPARATION: For best result surfaces should be dry and clean from stains, dirt, grease and other contaminants. New concrete should be re-bonded by OmegaSealer series 1000 coat (sealer base) if the surface is absorbent. Old chalky paints should be cleaned properly and re-bonded by OmegaSuperUndercoat or Omega Primer coat to insure proper base for new painting materials. For glossy surfaces or previous coatings should be roughened with sandpaper to make good inter-coat adhesion.

APPLICATION: Use good quality nylon brush, synthetic roller or airless spray.

THINNING, With clean water 10 – 20 % in some special cases thin up to 20 – 30 % when applying the first coat directly to unprimed absorbent surfaces or in hot climates.

COVERAGE, Each U.S. gallon should cover and interval between 40 – 55 m² depending on the texture absorption and color of the surface.

| | | | |
|--------------------|--------------------------|---------|----------|
| DRYING TIME | Dry to touch (Dust Free) | 30 – 60 | Minutes. |
| | Dry to re-coat | 4 - 6 | Hours. |
| | Dry to handle | 24 | Hours. |