

## **SuperOmegaPutty (series 100)**

*High Quality Putty Filler (sealer base)*

*Low paint absorption*

**CHARACTERISTICS**, sealer base putty filler specially formulated to be used on all types surfaces walls, ceiling and woodworks, help to hide walls defects by giving spreading layer with outstanding durability in various weathering conditions.

Resistance to alkalinity of concrete perfects adhesion and inter-coat adhesion (no need for sealer primer between layers in case of multi-layers usage) ease of application, non-toxicity extreme wash-ability, minimum absorbent finish scrub-able with salt and water and is free from disagreeable odor. It qualifies for safety painting slightly damp or permeable surface because it allows the humidity to pass through.

**SURFACE PREPARATION**, for best result surfaces should be dry and clean from stains, dirt, grease and other contaminants.

New concrete should be painted by OmegaSealer series 1000 coat (sealer base) if the surface is absorbent.

Old chalky paints should be cleaned properly and re-bonded by OmegaSuperUnder or OmegaPrimer coat to insure proper base for new painting materials. For glossy surfaces or previous coatings should be roughened with sandpaper to make good inter-coat adhesion.

**APPLICATION**, Use good quality stainless steel knife (should be flexible).

**THINNING**, usually none, if needed use up to 1 – 3 % clean water.

**COVERAGE**, Each U.S. gallon should cover and interval between 15 – 20 m<sup>2</sup> depending on the texture absorption.

<b>DRYING TIME</b>	Dry to touch (Dust Free)	4 – 6	Hours.
	Dry to re-coat	12	Hours.
	Dry to handle	24	Hours.